
# Profile SHP

## DECKING

### **Technical data**

Profile	SHP	m/m <sup>2</sup>	$m/m^3$
	26 x 92	10,20	418
	26 x 117	8,13	328
	26 x 140	6,85	274
Species:	Scandinavian Pine		
Length:	1.8 - 5.1 m		



### Regular decking

- Control Thermally modified
- For exterior and interior use
- Conventional and easy installation
- Cong-lasting
- 100% natural, reusable
- High dimensional stability

#### Additional Features







Thermal modification is a 100% natural method for increasing the durability and dimensional stability of wood, likewise for reducing water absorption. During the process, the wood is heated to a temperature of 180-220°C, while lowering the moisture content of the wood up to 4-6 %. Thermoarena conducts careful quality control of the wood before and after thermal modification. The lumber used for TM is checked and certified.



Please follow Thermoarena's installation instructions when working with thermal wood





Thermoarena OÜ, Farmi tee 5, Koigi küla, Järva maakond, 72501 Telefon +372 509 6803, info@thermoarena.com, thermoarena.com





